

**LISTING OF CLAIMS:**

This listing of claims will replace all prior versions and listings of claims in the application:

1. (Previously presented) A non-asbestos friction material comprising:

a fibrous reinforcement;

a friction modifier;

a binder; and

a soluble amorphous substance mixed as friction material components, wherein the soluble amorphous substance is a composition composed of  $\text{SiO}_2$  as a principal component, 18 to 40 wt% of at least one of  $\text{CaO}$  and  $\text{MgO}$ , less than 10 wt% of at least one of  $\text{Al}_2\text{O}_3$  and  $\text{ZrO}_2$ , and less than 2 wt% of at least one of  $\text{Na}_2\text{O}$ ,  $\text{K}_2\text{O}$ ,  $\text{FeO}$ ,  $\text{Fe}_2\text{O}_3$  and  $\text{BaO}$ .

2. (Original) The non-asbestos friction material according to Claim 1, wherein the soluble amorphous substance is mixed in a range of from 1 wt% to 30 wt% of a total of said friction material.

3. (Original) The non-asbestos friction material according to Claim 1, wherein the soluble amorphous substance is fibrous or granular.

4. (Original) The non-asbestos friction material according to Claim 1, wherein the soluble amorphous substance is formed of fibers having an average fiber diameter in a range of from 2  $\mu\text{m}$  to 9  $\mu\text{m}$  and an average fiber length in a range of from 100  $\mu\text{m}$  to 1,500  $\mu\text{m}$ .

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNER LLP

1300 I Street, NW  
Washington, DC 20005  
202.408.4000  
Fax 202.408.4400  
www.finnegan.com

5. (Original) The non-asbestos friction material according to Claim 1, wherein the soluble amorphous substance is formed of grains having an average grain size in a range of from 2  $\mu\text{m}$  to 100  $\mu\text{m}$ .

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNER <sup>LLP</sup>

1300 I Street, NW  
Washington, DC 20005  
202.408.4000  
Fax 202.408.4400  
[www.finnegan.com](http://www.finnegan.com)